

A transparent styrene-acrylic copolymer with sparkling clarity, good toughness and scratch resistance, that is easy to process.

- Rigid
- Easy to process
- Meets USP Class VI Plastics
- Excellent clarity
- FDA: 21 CFR 177.1830

### APPLICATIONS:

Injection molding items like drinkware, kitchen appliances, tableware, cosmetic packaging, medical devices, personal hygiene product packaging, office supplies, toys.

### PROPERTIES

PHYSICAL	Unit	Value	Unit	Value	TEST METHOD
Specific Gravity	g/cm <sup>3</sup>	1.03	lb/in <sup>3</sup>	0.04	ISO 1183
Melt Flow Rate (200 °C/5.0Kg)	g/10 min	10.0	g/10 min	10.0	ASTM D1238
<b>MECHANICAL</b>					
Tensile Strength, Break   0.2 in/min (5 mm/min)	psi	2,750	Mpa	19	ASTM D638
Break Elongation   0.2 in/min (5 mm/min)	%	150	%	150	ASTM D638
Tensile Modulus   0.2 in/min (5 mm/min)	psi	174,000	Mpa	1,201	ASTM D638
<b>IMPACT</b>					
Notched Izod (0.125 in / 3.175 mm)	ft-lbf/in	10.0	J/m	534	ASTM D256
<b>THERMAL</b>					
Vicat Temperature	°F	140	°C	60	ASTM D1525
HDT @ 264 psi (unannealed)	°F	158	°C	70	ASTM D648
<b>OPTICAL</b>					
Haze	%	4	%	4	ASTM D1003

Typical values represent average laboratory values and are intended as guides only, not as specific specification limits. Properties designated in this standard have been determined in accordance with the current issue of the specified testing methods.

### INJECTION MOLDING CONDITIONS

	°C	°F
Rear Barrel	160-170	320-338
Middle Barrel	170-180	338-356
Front Barrel	180-190	356-374
Nozzle	200-210	392-410
Mold	40	104
Maximum Recommended	250	482

### ADDITIONAL INFORMATION

Resirene's materials are biological and chemically inert. If possible recycling of final parts is recommended. If you require dispose it, follow indications established by government laws, related norms and the material safety data sheet.

#### WARNING:

Combustion of this material may cause hazardous fumes and gases that may be dangerous to one's health, especially in enclosed places. It should be noted that excessive heating or long residence times may cause degradation or yellowing.

#### NOTE:

The data contained herein is provided for information purposes only. By providing such information, Resirene, S.A. de C.V. makes no guarantee and does not assume any liability with respect to the accuracy or completeness of such information and the results obtained with this product in any specific instance; and hereby expressly disclaims all implied warranties of merchantability or fitness to a particular purpose. Nothing contained herein shall be construed as a license to use the products of Resirene, S.A. de C.V. in any manner that would infringe any patent.

**Resirene S.A. de C.V.**  
 Km 15.5 carret. Fed. Puebla-Tlaxcala  
 90780 Xicohtzinco, Tlaxcala, MEX  
 MEX toll free 01 800 RESINAS  
 USA toll free 1 866 372 3470

visit us at [www.resirene.com](http://www.resirene.com)