

TECHNICAL DATA SHEET

RESIRENE[®] HH 108

GENERAL PURPOSE POLYSTYRENE (GPPS)

FEATURES

- Medium Flow
- Heat Resistance
- Mechanical Resistance
- Free of zinc and oil additives
- FDA Rating: 21 CFR 177.1640

APPLICATIONS

- XPS insulation
- Extrusion
- Injection Molding

PROPERTIES					
Physical	English	Value	Metric	Value	Test Method
Melt Flow Rate (200°C/5.0 Kg)	g/10 min	2.6	g/10 min	2.6	ASTM D1238
Density	lb/ft ³	65	g/cm ³	1.04	ASTM D792
Mechanical					
Break Elongation	%	5	%	5	ASTM D638
Tensile Modulus	Kpsi	520	MPa	3,580	ASTM D638
Thermal					
Vicat Temperature	°F	216	°C	102	ASTM D1525
HDT @ 264 psi (unannealed)	°F	198	°C	92	ASTM D648
Ignition Characteristics					
Flammability	-	HB	-	<u>HB</u>	UL 94
Optical					
Light Transmittance	%	90	%	90	ASTM D1003

Properties reported in this data sheet are determined according to referred standard methods. Values shown represent averages from typical results measured in the laboratory and are provided only as a guide, not as specification limits.

EXTRUSION CONDITIONS

	°C	°F	
Initial zone	40	104	
Feeding zone	180-190	356-374	
Transport zone	190-200	374-392	
Compression zone	200-210	392-410	
Pumping zone	210-220	410-428	
Melt	250	482	

ADDITIONAL INFORMATION

Warning:

Combustion of this material may cause hazardous fumes and gases that may be dangerous to health, especially in enclosed places. It should be noted that excessive heating or long residence time may cause degradation or yellowing.

Note:

The data contained herein is provided for information purposes only. By providing such information, Resirene S.A de C.V. makes no guarantee and does not assume any liability with respect to the accuracy or completeness of such information and the results obtained with this product in any specific instance; and hereby expressly disclaims all implied warranties of merchantability or fitness to a particular purpose. Nothing contained herein shall be constructed as a license to use the products of Resirene, S.A. de C.V in any manner that would infringe any patent.

 MEX 01 800 RESINAS USA 1 866 372 3470
www.resirene.com